

AMENDMENTS TO THE CLAIMS

1. (Currently amended) In an anionic electrophoretic coating method in which a conductive substrate is contacted with [[an]] a basic electrophoretic coating bath composition and an electric current is imposed thereon to deposit a coating on the anode in the bath, the improvement comprising the coating composition being an equilibrated water based emulsion of ionic polymeric particles of nanometric size of between 10 and 100 nm and having a pH of 7.8 to 9 and a conductivity of 800-1500 $\mu\text{S}/\text{cm}$ and being essentially free containing about 1% or less of organic solvent.

2. (Canceled)

3. (Previously presented) The method according to claim 1, wherein the coating bath composition has a pH of 7.9 to 8.5 and a conductivity of 800 to 1300 $\mu\text{S}/\text{cm}^{-1}$.

4. (Previously presented) The method according to claim 1, wherein the coating bath composition does not contain an electrophoretically coatable pigment.

5. (Previously presented) The method according to claim 1, wherein the coating bath composition contains an electrophoretically coatable pigment.

6. (Previously presented) The method according to claim 1, wherein the coating bath composition contains about 1 to 30 weight percent solids.

7. (Previously presented) The method according to claim 1, wherein the coating is effected at room temperature employing a driving voltage of about 10 to 30 volts for about 15 to 60 seconds.

8. (Previously presented) The method according to claim 1, wherein the coating formed is baked.

9. (Original) The method according to claim 8, wherein the baking is effected at a temperature of about 100 to 180°C. for about 20 to 30 minutes.

10. (Original) The method according to claim 8, wherein the coating bath composition does not contain an electrophoretically coatable pigment.

11. (Original) The method according to claim 8, wherein the coating bath composition contains an electrophoretically coatable pigment.

12. (New) The method according to claim 3, wherein the coating bath composition contains about 1 to 30 weight percent solids.

13. (New) The method according to claim 12, wherein the coating is effected at room temperature employing a driving voltage of about 10 to 30 volts for about 15 to 60 seconds.

14. (New) The method according to claim 13, wherein the coating formed is baked.

15. (New) The method according to claim 14, wherein the baking is effected at a temperature of about 100 to 180°C. for about 20 to 30 minutes.

16. (New) The method according to claim 15, wherein the coating bath composition does not contain an electrophoretically coatable pigment.

17. (New) The method according to claim 16, wherein the coating bath composition contains an electrophoretically coatable pigment.